



## Specification – Aluspar

<b>Typical Analysis</b> (dry sample)	CaF <sub>2</sub>	55–65 %	
	Al <sub>2</sub> O <sub>3</sub>	20–25 %	
	MgO	0.5–1%	
	LOI	rest	
<b>Bulk Density</b>	700 kg/m <sup>3</sup>		*)
<b>Particle size distribution</b> (measured with laser diffraction)	> 30 µm	10–35 %	Typical 20 %
	5–30 µm	40–60 %	50 %
	< 5 µm	20–40 %	30 %
	< 2 µm	10–20 %	15 %
<b>Other Properties</b>	Aluspar is a precipitated calciumfluoride in the form of moist filter cakes. The product may be dusty in dry form due to small primary particles.		
	Colour:	Greyish/brownish (white when dry)	
	pH:	7–9 as 10 % slurry with water	
<b>Moisture at delivery</b>	typical	45 %	
	max	50 %	
	min	38 %	
*) The value is based on a small sample and may be higher at normal bulk transport quantities.			

# aluf fluor

HIGHER EFFICIENCY, LOWER IMPACT SINCE 1973

P.O. Box 902 SE-251 09 Helsingborg, Sweden

Tel +46 42 17 10 20 Fax +46 42 13 52 85 www.aluf fluor.com aluf fluor@aluf fluor.com